

# Technical data sheet

Product: **XPP56005**

Color: **white-blue**

Nominal size: **20x11,5 cm**

Declared size: **197x115x25 mm**

Surface: **relief matt**

Serie: **Pool**

Norm: **STO 030-059824**

Declaration: **P 02**

Group of goods: **sintered f.t.extruded-sp.shape**

Product type: **hand grip piece**

| Technical characteristics                | Norm                  | STO 030-059824                 | LB/RAKO                   |
|--|-----------------------|--------------------------------|---------------------------|
| Tolerance - Length/width                 | ISO 10545-2           | ± 2,0%                         | ± 2,0%                    |
| Tolerance - Thickness                    | ISO 10545-2           | ± 10%                          | ± 10%                     |
| Surface quality                          | ISO 10545-2           | Min. 95%                       | Min. 95%                  |
| Water absorption                         | ISO 10545-3           | E<0.5%,ind.max 0,6%            | E<0.5%,ind.max 0,6%       |
| Breaking strength                        | ISO 10545-4           | min. 600 N                     | >=1300 N                  |
| Modulus of rupture                       | ISO 10545-4           | Min. 28 N/mm <sup>2</sup>      | Min. 28 N/mm <sup>2</sup> |
| Resistance to deep abrasion (UGL)        | ISO 10545-6           | Max. 275 mm <sup>3</sup>       | Max. 275 mm <sup>3</sup>  |
| Resistance to surface abrasion (GL)      | ISO 10545-7           | Declared value                 |                           |
| Coefficient of linear thermal expansion  | ISO 10545-8           | Declared value                 | Max. 0,000008 / K         |
| Thermal shock resistance                 | ISO 10545-9           | Required                       | Resistant                 |
| Crazing resistance                       | ISO 10545-11          | Required                       | Resistant                 |
| Freeze-thaw resistance                   | ISO 10545-12          | Declared value                 | Satisfactory              |
| Durability for: internal use             | EN 14411              | Pass                           | Pass                      |
| Slipperiness (bare feet)                 | EN 16165              | Declared value                 | C                         |
| Slipperiness (shod feet)                 | EN 16165              | Declared value                 | Uncategorized             |
| Coefficient of friction (dry)            | EN 16165              | Declared value                 | >=0,7                     |
| Coefficient of friction (wet)            | EN 16165              | Declared value                 | >=0,6                     |
| Bond strength/adhesion-cem. adhesives    | EN 12004:2007+A1:2012 | Declared value                 | >=0,5 N/mm <sup>2</sup>   |
| Bond strength/adhesion-dispers. adhesiv. | EN 12004:2007+A1:2012 | Declared value                 | NPD*                      |
| Bond strength/adhesion-rea. resin adhes. | EN 12004:2007+A1:2012 | Declared value                 | NPD*                      |
| Bond strength/adhesion-mortar            | EN 12004:2007+A1:2012 | Declared value                 | NPD*                      |
| Moisture expansion                       | ISO 10545-10          | Declared value                 | 0,2 mm/m                  |
| Light reflectance value LRV              | ISO 10545-18          | Not required                   |                           |
| Impact resistance: Coef. of restit.      | ISO 10545-5           | Declared value                 | Min. 0,6                  |
| Reaction to fire                         | no testing 96/603 EHS | Class A1-A1FL                  | Class A1-A1FL             |
| Tactility                                | CEN/TS 15209          | Declare<br>surface description | Not relevant              |
| Resistance to staining                   | ISO 10545-14          | No visible changes             | No visible changes        |
| Resistance to low conc.of acids/alkalis  | ISO 10545-13          | Declared value                 | No visible changes        |
| Resistance to high conc.of acids/alkalis | ISO 10545-13          | Declared value                 | No visible changes        |
| Resist. to house. chem. and swim. pool   | ISO 10545-13          | Declared value                 | No visible changes        |
| Release of dang.subs.: Cadmium (GL)      | ISO 10545-15          | Declared value                 | NPD*                      |
| Release of dang.subs.: Lead (GL)         | ISO 10545-15          | Declared value                 | NPD*                      |
| Surface hardness according to Mohs       | EN 101                | Declared value                 | Min. 7                    |
| The reference life (RSL)                 | ISO 14 025/EN 15804   | 50 years                       | 50 years                  |
| Assessment of nat.radionuclide content   | CZ Imp.422/2016       | Max. index 1,0                 | Max. index 1,0            |

\* No Performance Determined – NPD